

United States Patent [19]
Chu

[11] **Patent Number:** **4,689,399**
[45] **Date of Patent:** **Aug. 25, 1987**

[54] **COLLAGEN MEMBRANES FOR MEDICAL USE**

[75] **Inventor:** **George Chu, Sunnyvale, Calif.**
[73] **Assignee:** **Collagen Corporation, Palo Alto, Calif.**

[21] **Appl. No.:** **840,312**

[22] **Filed:** **Mar. 13, 1986**

Related U.S. Application Data

[62] **Division of Ser. No. 685,350, Dec. 24, 1984, Pat. No. 4,600,533.**

[51] **Int. Cl.⁴** **C07G 7/00; A61L 15/04**

[52] **U.S. Cl.** **530/356; 128/156; 128/DIG. 8; 428/473**

[58] **Field of Search** **530/356; 128/82, 155, 128/156, DIG. 8; 428/473**

[56] **References Cited**

U.S. PATENT DOCUMENTS

2,934,446 4/1960 Highberger et al. 530/356
4,233,360 11/1980 Luck et al. 530/356
4,242,291 12/1980 Hughes et al. 264/1
4,412,947 11/1983 Cioca 424/116
4,453,939 6/1984 Zimmerman et al. 604/368
4,505,855 3/1985 Bruns et al. 128/DIG. 8

FOREIGN PATENT DOCUMENTS

0089152 9/1983 European Pat. Off. .
92200 10/1983 European Pat. Off. .
49-039174 6/1974 Japan .

Primary Examiner—Morton Foelak
Assistant Examiner—Nathan M. Nutter
Attorney, Agent, or Firm—Ciotti & Murashige

[57] **ABSTRACT**

A process for preparing collagen membranes useful in tissue repair, and wound healing and related membranous implant materials useful in both hard and soft tissue applications is disclosed. The resulting membranes and materials have properties which can be varied as desired to suit intended use. Variation results from altering the precise conditions of formation of the membrane or of related fibers and solids. The process comprises first forming a gel from solubilized collagen, followed by converting the gel into a one-, two- or three-dimensional membranous solid form. This conversion is performed either by applying pressure to the gel, or by disrupting the gel and separating the resulting precipitate for casting.

7 Claims, 2 Drawing Figures